

### Single Application Longevity - Dry road conditions test

\*Note - despite the test being 250w, which is greater than most average on training rides, the smooth nature of machine run seems to deliver much longer treatment lifespans vs real riding where the sinusoidal loading of pedalling action delivers much greater peak forces even for the same avg power, and the environment - like riding your ergo - has less airborne contamination. Real world road riding vs lab testing tends to indicate that lab test claims for treatment longevity may be around double to triple vs what may be assessed in field testing. ie in a lab test lubricant may hold its efficiency for 600km before notably increasing, yet on road the chain feels and sounds very dry by 300km and not pleasurable to ride past that point without relubricating / re-waxing. [For the Single application test, based on when some clear is beginning, real world training where treatment has moved from silky smooth zone etc, I would suggest real world results treatment lifespan at approx 1/3rd of wear jump point km's attained on test machine.](#) Note ZFC is always conservative re treatment lifespans - real world results will vary depending on your power, riding style, environment - conservative estimate is best as a guide just in case.

Lubricant	Km's to Jump Point	Km's to Wear allowance	Real world KM's Adjusted - Jump Point	Real World Km's to Wear allowance
Rex Black Diamond	5,602	5602	1,867	1867
Revolubes	3,416	3416	1,139	1139
Rex Black Diamond + Race Day Spray	3,415	3415	1,138	1138
AB Graphene Lube	3,254	3254	1,000	1085
Rex Domestique	3,210	3210	1,067	1067
Mspeedwax New Formula	1,800	3063	600	1021
Silca Synergetic	2,333	2333	778	778
Allied Grax	2,089	2089	696	696
Silca Hot Melt	1,300	1595	433	531
UFO Drip V2	900	1182	300	394
AB Graphene Wax	300	420	100	140

### Single Application Longevity - Dry Gravel / Mtb / CX

\*Note - despite the test being 250w, which is greater than most average on training rides, the smooth nature of machine run seems to deliver much longer treatment lifespans vs real riding where the sinusoidal loading of pedalling action delivers much greater peak forces even for the same avg power, and the environment - like riding your ergo - has less airborne contamination. Real world road riding vs lab testing tends to indicate that lab test claims for treatment longevity may be around double to triple vs what may be assessed in field testing. ie in a lab test lubricant may hold its efficiency for 600km before notably increasing, yet on road the chain feels and sounds very dry by 300km and not pleasurable to ride past that point without relubricating / re-waxing. [For the Single application test, based on when some clear is beginning, real world training where treatment has moved from silky smooth zone etc, I would suggest real world results treatment lifespan at approx 1/3rd of wear jump point km's attained on test machine.](#) Note ZFC is always conservative re treatment lifespans - real world results will vary depending on your power, riding style, environment - conservative estimate is best as a guide just in case.

Lubricant	Km's to Jump Point	Km's to Wear allowance	Real world KM's Adjusted - Jump Point	Real World Km's to Wear allowance
Rex Black Diamond + RDS	2,642	3071	880	1023
Mspeedwax New Formula	1,650	1848	550	616
Rex Black Diamond	1,476	1476	489	489
AB Graphene Lube	1,449	1449	483	483
Allied Grax	1,265	1551	421	517
Rex Domestique	1,154	1154	385	385
Revolubes	1,100	1588	367	529
Silca Hot Melt	900	1030	300	343
Silca Synergetic	500	690	167	230
Ufo Drip v2	450	1078	150	360
AB Graphene Wax	300	420	100	140

### Single Application Longevity - Extreme Conditions

\*Note - despite the test being 250w, which is greater than most average on training rides, the smooth nature of machine run seems to deliver much longer treatment lifespans vs real riding where the sinusoidal loading of pedalling action delivers much greater peak forces even for the same avg power, and the environment - like riding your ergo - has less airborne contamination. Real world road riding vs lab testing tends to indicate that lab test claims for treatment longevity may be around double to triple vs what may be assessed in field testing. ie in a lab test lubricant may hold its efficiency for 600km before notably increasing, yet on road the chain feels and sounds very dry by 300km and not pleasurable to ride past that point without relubricating / re-waxing. [For the Single application test, based on when some clear is beginning, real world training where treatment has moved from silky smooth zone etc, I would suggest real world results treatment lifespan at approx 1/3rd of wear jump point km's attained on test machine.](#) Note ZFC is always conservative re treatment lifespans - real world results will vary depending on your power, riding style, environment - conservative estimate is best as a guide just in case.

Lubricant	Km's to Jump Point	Km's to Wear allowance	Real world KM's Adjusted - Jump Point	Real World Km's to Wear allowance
AB Graphene Lube	600	807	200	270
Silca Synergetic	500	690	167	230
Silca Hot Melt	300	637	100	212
Mspeedwax New Formula	300	588	100	196
Rex Black Diamond	300	538	100	179
Rex Black Diamond + RDS	300	525	100	175
Allied Grax	300	450	100	150
Rex Domestique	300	427	100	143
AB Graphene Wax	200	344	66	115
Ufo Drip v2	150	357	50	119